



60141

PRODUCT INFORMATION:

60141 is a medium weight, low viscosity putty excellent for radius, fairing, bedding or bonding.

GENERAL PROPERTIES:

Viscosity:	Stable paste
Catalyst:	MEK Peroxide
Shelf Life:	6 months (stored out of sun)
Pot Life:	18 to 30 minutes with 1.5% DDM-9 at 76 deg. F
Weight/Gallon:	8.1 - 8.7
Chemically:	Polyester resin and fillers
Flash Point:	Closed cup 89 deg. to 90 deg. F.

USES FOR 60141:

- Power craft
- Sailboats
- Yachts
- Mobile homes
- Travel trailers
- Truck cab
- Automotive
- Most other fiberglass applications

Notice: This information is presented in good faith, but no warranty expressed or implied is given. The information, to our best knowledge, is true and accurate, but all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control.

Revised October 2019

DBF, Inc. 18576 Krause PO Box 2385 Riverview, MI 48193
Phone: 734-285-1480 Fax: 734-285-1481 Website: dbf-inc.com Email: custserv@dbf-inc.com