



60750

Product Information

60750 is a white, thixotropic polyester compound for blister repair that is designed to spread smoothly for ease of application. It can be used where higher heat distortion temperatures are needed than standard putties can provide. 60750 can be catalyzed with MEKP or BPO cream hardener. It is an excellent fairing compound and final finish compound.

GENERAL PROPERTIES:

Viscosity:	Non-flowing Paste
Shelf Life:	6 months (stored out of sun)
Pot Life:	1:45 to 6 minutes with 1% DDM-9 at 76 deg. F 2 to 6 min. with 2% BPO Paste (50%) at 76 deg. F.
Weight/Gallon:	13.3 to 13.8 pounds
Sp. Gr.	1.6 to 1.65
Chemically:	Polyester resin and fillers

USES FOR 60750:

- Power craft (OEM and repair)
- Sailboats
- Yachts
- Mobile homes
- Travel trailers
- Truck cab
- Tooling
- Most other fiberglass applications

Notice: This information is presented in good faith, but no warranty expressed or implied is given. The information, to our best knowledge, is true and accurate, but all recommendations or suggestions are made without guarantee since the conditions of use are beyond our control.

Revised November 2019

DBF, Inc. 18576 Krause PO Box 2385 Riverview, MI 48193
Phone: 734-285-1480 Fax: 734-285-1481 Website: dbf-inc.com Email: custserv@dbf-inc.com